

# MASTERFILL UF 118



## Performance Benefits and Overview

UF 118 content contains talc powder, resin and some additives. It's suitable for injection application. The purpose of using this grade is to reduce cost for the end product and improve some properties such as whiteness, hardness, strength.

CaCO <sub>3</sub> Powder Content	88±1 %
Partical Size	3 µm
Carrier Resin	LLDPE
Purity	96-98%
Mean particle size (D50)	5 µm (450 mesh)
Melt Mass- Flow Rate (190°C/2.16kgs)	1-3 g/10 mins
Humidity	<0.08 wt %
Bulk Density	1.15 g/cm <sup>3</sup>
Processing Temperature	140-280°C

### Main Features

Good Dispersion	✓
Gloss Finish	✓
Food Contact	✓
Good Processability	✓
High Light Fastness	✓
Excellent Heat Resistance	✓
Increase Hardness	✓

Depending on processing parameters or local specifications. It is advisable to check with our sales to commercial production.

UF 108	Polymer Compatibility			
	LLDPE	HDPE	LDPE	PP
	✓	✓	✓	✓

Standard Packaging	Certificate
25 kg bags (pallet 1350kg) Jumbo Bag ( 1200 kg)	FDA, REACH, ISO 1900-2015

Main Application	Properties	Dosage
Blow Film (Roll bags, T-shirt bags, Garbage bags)	PE Film thickness from 30 micron	Upto 30 %
	PE Film thickness from 40 micron	Upto 40 %
Injection Molding (HDPE Crates)		Upto 10 %
HDPE Blow Molding ( Jerry cans/bottles)		Upto 10 %

The product should be stored in dry conditions at temperatures below 25°C protected from direct sunlight. If these protective measures are not taken into account impairment of the product is possible. This can result in degradation of the color, smell or loss of other properties. The data and information contained are presented in good faith, and are based on USMASTERBATCH's current knowledge and experience. They are provided for guidance only. Because many factors may affect processing or application/use of the product. USMASTERBATCH recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to us.

FOR & ON BEHALF OF

**US MASTERBATCH JOINT STOCK COMPANY**